

Interlam Akupanel Report of Surface Burning Characteristics

Fire Test: The PET backer has a Flame Spread Index of 0 and a Smoke Developed Index of 350. The black thru colored MDF has a Flame Spread Index of 15 and a Smoke Developed Index of 5. Class A classification has Flame Spread Index of 0-25 with Smoke Developed Index of 0-450.

****Architects & Designers please contact if a full test report is needed for your specbook**